

toner plastics

Technical Data Sheet

TPU

Effective Date: 11/02/2020

Revision Number: 01

<i>Physical Properties</i>	<i>Standard</i>	<i>Unit</i>	<i>Typical Value</i>
Density	ISO 1183	g/cc	1.20

<i>Mechanical Properties</i>	<i>Standard</i>	<i>Unit</i>	<i>Typical Value</i>
Tensile Strength, Break	ISO 527	MPa	55.2
Tensile Elongation, Break	ISO 527	%	580
Tensile Modulus	ISO 527	MPa (@ 100% - 300%)	7.8 - 18.6
Flexural Modulus	ISO 178	MPa	250
Flexural Strength	ISO 178	MPa	N/A

<i>Thermal Properties</i>	<i>Standard</i>	<i>Unit</i>	<i>Typical Value</i>
Glass Transition Temperature (Tg)	DSC	°C	-45
Heat Deflection Temperature (HDT)	ISO 75	°C (@ 0.45 MPa)	N/A

<i>Hardness Properties</i>	<i>Standard</i>	<i>Unit</i>	<i>Typical Value</i>
Shore Hardness	DIN 53505	A	90

Disclaimer: The technical data contained on this data sheet is furnished without charge or obligation and accepted at the recipient's sole risk. This data should not be used to establish specifications limits or used alone as the basis of design. The data provided is not intended to substitute any testing that may be required to determine fitness for any specific use.